



EQUIPMENT/MATERIALS

Use a grout mixer blade, 3/4" heavy duty drill and a 5-gallon pail (for mixing). One mix equals 4.2 mixed gallons.

Notes:

- A. Equipment and tools should be sprayed with silicone release agent prior to use.
- B. Do not install PaveSaver™ when any moisture is present or when pavement temperatures are below 50°F (10°C) or above 110°F.

AREA PREPARATION

Chip and/or saw all loose concrete, leaving only sound concrete. Carefully sandblast and blow out all areas which will be in contact with PaveSaver™.

MIXING

Mix 1750 ml (4.0 lbs) of Part A* and 2000 ml (4.0 lbs) of Part B* for 30-60 seconds. Add two pre-weighed 27.5 lb. bags of the aggregate blend and continue to mix. When properly mixed, PaveSaver™ is an even color.

* Note: Parts A and B volumes are different.

POURING

Fill entire area to grade as you go - PaveSaver™ is self-leveling.

TEXTURING

As it cures, use a trowel to achieve a grooved or textured finish. Masking and forming materials which were used should be removed immediately after troweling.